


Cross Section

Soft melamine foam with profiled surface (grey)



Close-up



Applications

- Machinery jacketing
- Motor vehicles
- Machinery
- Acoustics

Attributes

Dinaphon® B 840 absorption sheets have excellent absorption properties and are highly resistant to many chemical substances.

Melamine foam has different sized pores with a maximum of 10 pores of 5 - 15 mm diameter per square metre. Dimensional deviation of up to 1.5 % in the length and width may occur and is acceptable.

Application

Dinaphon® B 840 sheets easily cut to size with a sharp knife.

Storage

Store in a dry area at temperatures ranging between 15 - 25° C.

Technical Data

Product Data	Dinaphon® B 840
Bulk density of foam	8.5 – 11.5 kg/m³
Thermal stability:	
Foam	- 60 to + 150 °C
Fire ratings as per DIN 5510Section 2	S4, SR2, ST2
Building material rating of foam as per DIN 4102	B1
BKZ (Swiss fire code rating)	5.3
Rated thermal conductivity λ (W/m²K)	0.035

Packaging Unit and Form

Sheet size:	1200 x 600 mm
Sheet thickness:	30 mm
Product variant designation:	B 840/30


Cut to order sheets:

Keller will be glad to cut sheets to specific size requirements indicated in customer plans or drawing files for both small and large orders. Ask for a price quote.

Sound Absorption

Results obtained using the reverberant field testing method:

	30 mm
100 Hz	0.06
125 Hz	0.05
160 Hz	0.07
200 Hz	0.13
250 Hz	0.23
315 Hz	0.34
400 Hz	0.45
500 Hz	0.55
630 Hz	0.66
800 Hz	0.72
1000 Hz	0.80
1250 Hz	0.85
1600 Hz	0.90
2000 Hz	0.95
2500 Hz	0.93
3150 Hz	0.92
4000 Hz	0.95
5000 Hz	0.97



Keller Lärmschutz AG provides its assistance, application-specific advice and product use instructions to the best of its knowledge and ability. Keller Lärmschutz AG reserves the right to make the changes to its products and information, which are the result of its constant efforts to improve both the information and products, and shall not be held liable for damages occurring due to the

information or assistance it provides. Moreover, the information provided by Keller Lärmschutz AG shall not nullify the responsibility of the purchaser of the products to test the suitability of the materials for the intended application, process and purpose prior to using them.